

Sunlite & Litespal Laminate 1.0mm BS 476: part 7 Flame Test

2.0 <u>Description of Samples</u>

Details of the manufacture product provided by the client:

Product Type : High Pressure Decorative Laminate
Type of Composition/Ingredient : Papers Treated with Resin/ Malamine

Brand/Model/Serial No. : Litespal/ Sunlite
Manufacture/Name : Sunflower Corporation

Nominal thickness of sample : 1.0mm

6.0 Result of Test

Specimen No.	1	2	3	4	5	6
Spread of flame at first 1 1/2 minutes (mm)	0-75	0-75	0-75	75-165	0	0-75
Distance (mm)	Time of spread of flame to indicated distance (minutes • seconds)					
Start of flaming	0.21	0.26	0.22	0.19	Nil	0.24
75			2.13	1.28		
165						
190						
215						
240						
265						
290						
375						
455						
500						
Time of maximum						
spread of flame	1.41	0.30	2.45	5.06		1.23
(minutes • seconds)						
Distance of						
maximum spread of	0-75	0-75	75-165	75-165	0	0-75
flame (mm)						
Comments	None					

7.0 Conclusion

In accordance with the class definitions specified in the Standard, the test results show that the sample tested has a <u>Class One</u> Surface Spread of Flame.

Classification of Surface Spread of Flame

Classification	Spread	of flame at 1.5 min.	Final spread of flame			
	Limit (mm)	Limit for one specimen in sample (mm)	Limit (mm)	Limit for one specimen in sample (mm)		
Class 1	165	165 + 25	165	165 + 25		
Class 2	215	215 + 25	455	455 + 45		
Class 3	265	265 + 25	710	710 + 75		
Class 4	Exceeding the limits for class 3					